




PO Box 31126  
Dayton, OH 45437  
Tel: 937.252.2989 Fax: 937.258.3937  
E-mail: info@exciton.com  
www.exciton.com

## IRA 931: Infrared Absorber

### Properties

Composition	Proprietary Coordination Complex <sup>1</sup>
Peak Wavelength	926 ± 1 nm (methylene chloride); 939 ± 1 nm (polycarbonate)
Strength	55 L/gm-cm (methylene chloride)
Appearance	Black crystalline solid
Solubility	2.32 grams/liter (chloroform), 1.46 grams/liter (methylene chloride), 0.23 grams/liter (toluene), 0.1 grams/liter (methyl ethyl ketone)
Melting Point	> 300 °C
Solar Stability	Good

### Spectrum (methylene chloride)



1. This product is offered by Exciton, Inc. under non-analysis and may be available for licensing for specific applications that require selective absorption and high temperature stability. Please contact Exciton for licensing or additional technical information.

The information presented above is believed to be accurate but is not a specification. The customer is fully responsible for determining the suitability of this product for use in their application. Exciton, Inc. does not represent that the information is sufficient or complete for any specific application.